

## Ar pārejas metālu joniem aktivēta CaAl<sub>12</sub>O<sub>19</sub> optiskās īpašības

Pāvels Rodionovs<sup>1</sup>, Meldra Ķemere<sup>1</sup>, Andris Antuzevičs<sup>1</sup>, Uldis Rogulis<sup>1</sup>, Andris Fedotovs<sup>1</sup>,  
Maja Szymczak<sup>2</sup>, Lukasz Marciniak<sup>2</sup>, Anatolijs Šarakovskis<sup>1</sup>

<sup>1</sup>*Latvijas Universitātes Cietvielu fizikas institūts*

<sup>2</sup>*Polijas Zinātņu akadēmijas Zemo temperatūru un struktūras pētniecības institūts*

Kalcija heksaalumināts (CaAl<sub>12</sub>O<sub>19</sub>) ir ar alumīniju bagātākais savienojums CaO-Al<sub>2</sub>O<sub>3</sub> sistēmā. Tam ir raksturīga magnetoplumbīta struktūra ar piecām atšķirīgam alumīnija pozīcijām kristālrežģī, kas nodrošina materiāla optisko īpašību daudzveidību, aktivējot to ar kādu no pārejas metālu joniem (Cr<sup>3+</sup>, Fe<sup>3+</sup>, Mn<sup>4+</sup>, Mn<sup>2+</sup>, Ti<sup>3+</sup>, Ti<sup>4+</sup>, vai Ni<sup>2+</sup>).

Šajā darbā tika pētītas ar Cr<sup>3+</sup>, Fe<sup>3+</sup>, un Mn<sup>2+</sup> aktivētu CaAl<sub>12</sub>O<sub>19</sub> optiskās īpašības izmantojot tādas spektroskopiskās metodes kā fotoluminiscence (emisija, ierosme, kinētika, atkarība no temperatūras vai spiediena) un elektronu paramagnētiskā rezonanse. Ar Cr<sup>3+</sup> aktivētajos paraugos tika identificētas trīs spektrālās komponentes: divas šauras emisijas joslas ar maksimumiem pie 689 un 700 nm, un plata emisijas josla ar maksimumu pie 785 nm. Ar Fe<sup>3+</sup> aktivētajos CaAl<sub>12</sub>O<sub>19</sub> ir novērota luminiscence tuvajā infrasarkanajā spektra diapazonā ar maksimumu pie 810 nm. Savukārt, paraugos ar Mn<sup>2+</sup> joniem ir redzama zaļa luminiscence ar maksimumu pie 518 nm.

Balstoties uz pētījumā iegūtiem datiem, tika spriests par sakarību starp materiāla struktūru un tā optiskām īpašībām, kā arī piedāvāta stratēģija Mn<sup>2+</sup> luminiscences intensitātes uzlabošanai.

## Optical properties of transition metal-doped CaAl<sub>12</sub>O<sub>19</sub>

Pavels Rodionovs<sup>1</sup>, Meldra Kemere<sup>1</sup>, Andris Antuzevics<sup>1</sup>, Uldis Rogulis<sup>1</sup>, Andris Fedotovs<sup>1</sup>,  
Maja Szymczak<sup>2</sup>, Lukasz Marciniak<sup>2</sup>, Anatolijs Sarakovskis<sup>1</sup>

<sup>1</sup>*Institute of Solid State Physics, University of Latvia*

<sup>2</sup>*Institute of Low Temperature and Structure Research Polish Academy of Sciences*

Calcium hexaaluminate (CaAl<sub>12</sub>O<sub>19</sub>) is the most Al-rich phase in CaO-Al<sub>2</sub>O<sub>3</sub> system. It exhibits magnetoplumbite-type structure that contains five distinct Al crystallographic sites with different degrees of local symmetry. Such feature allows to accommodate various transition metal ions (Cr<sup>3+</sup>, Fe<sup>3+</sup>, Mn<sup>4+</sup>, Mn<sup>2+</sup>, Ti<sup>3+</sup>, Ti<sup>4+</sup>, Ni<sup>2+</sup>) that show diverse optical properties.

In this work, we review optical properties of Cr<sup>3+</sup>, Fe<sup>3+</sup>, and Mn<sup>2+</sup> doped CaAl<sub>12</sub>O<sub>19</sub> by employing spectroscopic techniques such as photoluminescence (emission, excitation, kinetics, temperature or pressure dependence) and electron paramagnetic resonance. In the Cr<sup>3+</sup> doped CaAl<sub>12</sub>O<sub>19</sub> samples three different Cr<sup>3+</sup> spectral components have been identified: two red narrow-band emission with maxima at 689 and 700 nm, and wideband emission peaking at 785 nm. Fe-doped CaAl<sub>12</sub>O<sub>19</sub> exhibits near infrared emission with maximum at 810 nm, while Mn<sup>2+</sup> doped samples emit green light with maximum at 518 nm.

Based on the findings, the relationship between material structure and its optical properties is discussed, strategy to improve Mn<sup>2+</sup> luminescence intensity is suggested as well.